

CARBON BEAM 35/150

DESCRIPTION

35 Stitch-Bonded Uni-Directional Carbon Fabric is produced from Continuous Tow Carbon Fiber. Unique fiber spreading techniques are utilized to obtain the correct UD fabric weight.

Manufacturer

CPR Products, Inc.
 1315 West Lark Ind. Park.
 St. Louis, MO 631026
 Telephone: [636] 717-0666
 Fax: [636] 717-0665
 Toll Free: [888] 531-8940

Benefits

- Economical
- Low profile repair
- Adds structural integrity
- Can be used in conjunction with crack injection

How to use

Surface Preparation: Surface must be clean and sound 13-14 inches wide in area of installation. May require grinding to obtain exposure to solid concrete. Remove all dirt, grease, wax, curing compounds and other foreign matter. Remove water and dust from all surfaces prior to application. Prepared surface area should be vertical to wall and no more than five feet apart.

PROPERTIES OF CARBON BEAM 35/150		
PRODUCT COMPONENTS (all weights in grams per square meter)		
UD 150	158	
Glass 34 tex	10	
Polyester Veil	-	
Polyester Stitch 76 dtex	6	
Binder resin Powder	8	
FABRIC CONSTRUCTION		
Stitch Length	3.6mm	
Stitch Pattern	Tricot	
Dry Thickness	0.4mm	
Sheet Size	12"x24"	
FIBER PROPERTIES		
Tensile Strength	213 kpsi	(213,000 psi)
Tensile Modulus	16.7 Mpsi	(16.7 million psi)
Compressive Strength	113 ksi	(113,000 psi)
Compressive Modulus	15.8 msi	(15.8 million psi)
Density	0.065lb/in	
Fiber Diameter	0.283 mils	
Carbon Content	95 %	
(Based on Fiber Volume Fraction (FVF) of 55%)		

Installation:

Center each piece of the carbon fiber vertically to wall within the prepared area. Fabric toes must be vertical to wall. Be certain to get complete surface contact with #500 Bonding Epoxy already

applied to the full length of repair area. Roll out all air pockets using a thin nap roller in the vertical direction of the toes. Apply a second coat of #500 over the entire fabric area using the same vertical motion. Allow to cure.

CPR PRODUCTS, INC.

1315 West Lark Ind. Park St. Louis, MO 63026 Phone 636-717-0666 Toll Free 888-531-8940

Packaging

Carbon Beam consist of:
100 lineal foot x 12 inch wide
roll of Carbon Fiber.

Limitations/Precautions

- Temperature of substrate must be above 40°F.
- New Concrete must be at least 28 days old.

Storage

Carbon Beam should be stored in a dry environment between 60-80 deg. F.

Technical Service

Complete technical service and specification services are available from the manufacturer and their authorized representatives.

Warranty

All recommendations, statements and technical data contained herein are based on tests we believe to be reliable and correct. CPR Products, Inc. warrants its products to be free of manufacturing defects and that at the time and/or place of shipment our material will meet current published physical properties when applied with ASTM and CPR Products, Inc. standards. CPR Products, Inc. liability is limited to the replacement of the material if found to be defective. As CPR Products, Inc. has no control of the use to which others may put its products, it is recommended the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect, engineer, contractor and the owner for the design, application and proper installation of each product. Nothing contained herein shall be construed to be a recommendation to use or as a license to operate under or to infringe any existing patents.

CPR PRODUCTS, INC.

1315 West Lark Ind. Park, St. Louis, MO 63026 Phone 636-717-0666 Toll Free 888-531-8940